

**PLASCON ROOF PAINT**

**PRODUCT DESCRIPTION AND USES**

Based on a flexible alkyd and inert pigments, Plascon Roof Paint offers maximum protection for galvanized roofs and exposed Iron and Steel structures. As a flexible film coating, Plascon Roof Paint will withstand extreme weather variation and the resultant dimensional changes. It offers high opacity.

**SURFACE PREPARATION**

**New GCI Roof**

Allow the surface to etch by weathering (i.e. 6 months) or treat with Mordant solution prior to application of Roof Paint. Alternatively prime with Plascon Wash Primer or Zinc Phosphate primer. Ensure the surface is clean and dry. Apply 2 coats of Plascon Roof paint.

**Previously Painted Surfaces**

Remove all loose and flaky materials. Patch prime bare metal surfaces with Etch Primer or Plascon Zinc Phosphate Primer. Apply 1-2 coats of Plascon Roof Paint.

**FINISH**

Semi gloss

**APPLICATION**

Brush, roller or spray.

**THINNING AND MIXING**

White Spirit for brush application and/or Synthetic Thinner for spray application.

**EQUIPMENT CLEANING**

Clean the equipment immediately after use with White Spirit.

**DRYING TIME**

Dust dry in 15 minutes. Hard dry in 2-4 hours.

**COLOUR RANGE**

Red oxide, chrome green, white and grey.

**SPREADING CAPACITY**

9m<sup>2</sup> (100ft<sup>2</sup>) per litre/ 35 microns DFT

**PACK SIZES**

1 Litre, 4 Litres and 20 Litres.

